

Primary high temperature lithium battery

ER30820S

3.6 V Primary lithium-thionyl chloride (Li-SOCl₂)
30MM-sized cell for operation up to 165°C

Benefits


- High voltage response, stable during most of the lifetime of the application
- Ability to perform safely and reliably up to 165°C with severe vibration/shock constraints
- Long shelf life
- Low self-discharge, compatible with a long operating life (less than 1% per year of storage, at +25°C, after 1 year)
- Superior resistance to corrosion
- Easy integration into compact systems

Key features

- Primary chemistry (non-rechargeable)
- Spiral Construction High rate
- Hermetic glass-to-metal sealing engineered for leak free operation
- Sturdy and pressure resistant 304 stainless steel envelope
- Ability to withstand at 165°C extreme shocks and vibration
- Custom terminations available
- ISO9001 ISO14000

Main applications

- MWD, LWD, Oil Well Instrumentation
- Downhole Electronic Control System
- Wireless Drilling System
- Well logging, Inclination and other instruments
- Coalbed methane, Geothermal, Geophysical prospecting
- Military communications



Cell size references

Electrical characteristics

[Typical values relative to cells stored up to one year at + 30°C max]

Open circuit voltage(at+25°C)	3.65V
Nominal capacity (under 50mA, +25°C, 2.0 V cut-off) (The capacity restored by the cell varies according to current drain, temperature and cut-off)	13Ah
Nominal voltage (under 0.1 mA, +25°C)	3.6V
Rate Current	H: 400mA, M: 150mA
Max. Continuous Discharge Current	300~600mA
Storage temperature (recommended)	≤ 30°C
Operating temperature range	-40/+165°C (-40/329°F)

Self Discharge Rate

(Low self-discharge, compatible with a long operating life
less than 1% per year of storage, at +25°C, after 1 year)

1% per year

Physical characteristics (unsleeved cells)

Diameter(nominal)	30mm
Length(nominal)	80mm
Weight	125g

Jinhengyuan Electronic Technology Co., Ltd

Specialty High Temperature Battery

No.7 Liangtian South Hengyi Road

Baiyun, Guangzhou, China

Tel: 0086 18671014147

0086 18666606407

www.gaobitebattery.com

Warning

- Fire, explosion and burn hazard
- Do not recharge, short circuit, crush, disassemble, heat above 180°C (356°F), incinerate, or expose contents to water
- Do not solder directly to the cell (use tabbed cell versions instead)



Reference

Gaobite is the high-temperature battery brand belongs to Jinhengyuan Electronic Technology Co., Ltd. Information in this document is subject to change without notice and becomes contractual only after written confirmation by Gaobite. The information on this datasheet is for marketing purposes only. Please consult with Gaobite for more information regarding how our cells will perform within your application. The information in this document is subject to change without notice and does not constitute a warranty of performance. The length dimension was unsleeved. The use of terminations will impact overall cell length. Diameter measurements Does not include label or shrink. The "Main Application" list does not include all potential applications, please consult Gaobite for